

TECHNICAL DATA SHEET No.247

Lawirostal Epoxi-Härter

Hardener component

I. Product

High quality hardener component for einZA Lawirostal 2-K-Epoxi-Primer.

Processing of the hardener component of einZA (mix) Lawirostal 2-K-Epoxi-Primer only in combination with the master batch.

For further notice please see Technical Data Sheet no. 010.



II. Technical data

Density (20°C)	0.900 = 900 g/cm ³
Colour shade	odourless liquid

III. Working instructions

Mixing ratio	master batch : hardener = 4 : 1 volume % master batch : hardener = 6.5 : 1 weight %
--------------	--

Processing	The packages of einZA (mix) Lawirostal 2-K-Epoxi-Primer have the exact quantities of master batch and hardener. Add the hardener to the master batch and stir mechanically with a stirrer till a homogenous compound arises. We recommend to decant and mix the compound once before processing ("Umtopfen").
------------	---

Cleaning of tools	with einZA Universal-Nitroverdünnung
-------------------	--------------------------------------

IV. Security advice and labeling

The product is subject to the Ordinance on Hazardous Substances.

All necessary advices are included in the Safety Data Sheet according to the CLP regulation (GHS) corresponding the regulation (EG) no. 1272/2008. At any time available at www.einZA.com or to be requested by sdb@einZA.com.

Labeling notes on the container labels have to be considered !

The details given above have been compiled in accordance with knowledge of state-of-art testing technology and are to be considered as directives. Because of the manifold methods of application and working these are without commitment and give no grounds for any contractual legal relationship and, moreover, do not release the user from testing our products as to their suitability at his own responsibility. In all other respects our general terms of business are valid. **Issued 10/2020**; as a result of which all previous memorandum sheets become invalid.